



## PRODUCT DATA SHEET



### EKO INSULATING OIL UNH Transformer oil

#### DESCRIPTION

EKO INSULATING OIL UNH is a high quality naphthenic transformer oil without antioxidant additives (uninhibited), suitable for oil switches and high voltage transformers.

EKO INSULATING OIL UNH presents high oxidation stability, very good dielectric properties and a very satisfactory heat transfer.

#### SPECIFICATIONS

IEC 60296, ed. 4, 2012, general specifications.

#### TYPICAL CHARACTERISTICS

Properties	Units	Methods	EKO INSULATING OIL UNH
Density at 20°C	g/ml	ISO 12185	0.882
Viscosity at 40°C	cSt	ISO 3104	9.9
Viscosity at -30°C	cSt	ISO 3104	1162
Flash point (PMCC)	°C	ISO 2719	146
Pour point	°C	ASTM D5950	-49
Acidity	mg KOH/gr	IEC 62021-1	<0.01
Corrosive sulfur		DIN 51353	Non corrosive
Corrosive sulfur		ASTM D1275	Non corrosive
Corrosive sulfur		IEC62535	Non corrosive
Dielectric Dissipation Factor (DDF) at 90°C		IEC 60247	0.001
Interfacial tension	mN/m	ASTM D971	45
Breakdown voltage, before treatment, 2.5mm	kV	IEC 60156	55
Breakdown voltage, after treatment, 2.5mm	kV	IEC 60156	75



## PRODUCT DATA SHEET



### TYPICAL CHARACTERISTICS

Properties	Units	Methods	EKO INSULATING OIL UNH
Oxidation stability at 120°C, 164 hours			
Total acidity	mg KOH/gr	IEC 61125, C	0.6
Sludge	%	IEC 61125, C	0.2
DDF at 90°C		IEC 61125, C	0.044
PCA content	%	IP 346	<3
PCB content	mg/kg	IEC 61619	Not detected
Antioxidants	%	IEC 60666	Not detected

### HEALTH AND SAFETY

Protect the environment while disposing of used product. Used lubricants should be collected at specific points to ensure they do not pollute the environment. Do not mix with solvents, brake fluids, antifreeze and water, to allow for proper handling.

Issue 4, 18 February 2019

This data sheet provides basic information on the product as at the date of drafting. For further information regarding applications, please contact EKO ABEE Technical Support, tel. +30 210 5509 511 and +30 210 7725 418. Advice on safe handling is provided in the Safety Data Sheet.