



## PRODUCT DATA SHEET



### EKOGREASE GP 2 Lithium/calcium grease

#### DESCRIPTION

EKOGREASE GP 2 is a lithium/calcium grease enhanced with specially designed additives that ensure extended operating life compared to conventional multi-purpose grease products.

Thanks to its excellent adhesion properties, EKOGREASE GP 2 provides grease performance efficiency under severe moisture or humidity conditions, including the presence of steam.

#### SPECIFICATIONS

DIN 51825 KP2K-25.

#### APPLICATIONS

- The product is suitable for the lubrication of heavy-type equipment used in construction, mining and quarrying, and can be used in environments containing water, mud and dust.
- It is suitable for heavy load industrial applications where washout by water is a possibility.
- Thanks to its mixed lithium/calcium soap and the high viscosity of its base oil, EKOGREASE GP 2 is suitable for the lubrication of rolling-element bearings carrying heavy loads at low speeds.

#### ADVANTAGES

- Outstanding resistance to washout by water.
- Excellent adhesion to metal surfaces.
- Increased lubrication ability and mechanical stability at a wide range of operating temperatures from -20°C to +120°C.



## PRODUCT DATA SHEET



### TYPICAL CHARACTERISTICS

Properties	Methods	Units	EKOGREASE GP 2
Soap base	-	-	Lithium/Calcium
Base oil	-	-	Mineral oil
NLGI	-	-	2
Colour	Visual Inspection	-	Red
Base oil viscosity at 40°C	ASTM D 445	cSt	300
Dropping point	ASTM D 566	°C	175
Worked penetration 60 strokes	ASTM D 217	mm <sup>-1</sup>	265-295
Water washout, max.	ASTM D 1264	% w/w	10
TIMKEN Test OK Load, min	ASTM D 2509	lbs	45
4 ball wear test, mm, max	ASTM D 2266	mm	0.60
4 ball weld load	ASTM D 2596	kg	250
Copper corrosion, max.	ASTM D 4048	-	1b
Operating temperature	-	°C	-25°C to +130°C

### HEALTH AND SAFETY

Protect the environment while disposing of used product.

Issue 3, 3 January 2018

This data sheet provides basic information on the product as at the date of drafting. For further information regarding applications, please contact EKO ABEE Technical Support, tel. +30 210 5509 511 and +30 210 7725 418. Advice on safe handling is provided in the Safety Data Sheet.