

EKO MARINE PLUS 20W-50

Lubricant for marine 4-stroke diesel engines

Description

EKO MARINE PLUS 20W-50 is a high-performance multigrade heavy-duty diesel engine oil, suitable for use mainly in older or reconditioned high-speed four-stroke marine diesel engines operating on coastal shipping, fishing, leisure boats and other applications. It is suitable for both naturally aspirated and turbo-charged diesel engines.

Specifications

ACEA E2, API CF-4/SH, MB 228.1, MAN 271.

Applications

- High-speed 4-stroke marine diesel engines, where SAE 20W-50 lubricants of ACEA E2, API CF-4 or lower quality level are required.
- Applications include coastal vessels, fishing boats, lifeboats and leisure boats.
- •High-speed engine generators.
- Transmission systems and auxiliary units, according to manufacturer's recommendations.

Advantages

- High resistance to shear: maintains a strong lubricating film at high operating temperatures.
- Water resistance: helps maintaining a strong lubricating film in the presence of seawater.
- Control of deposits and sludge: helps maintaining cleanliness of the engine.
- Strong protection against wear: increases the lifespan of all critical engine components.

Typical Characteristics

Properties	Methods	Units	EKO MARINE PLUS 20W-50
SAE Viscosity Grade	-	-	20W-50
Density, 15°C	ASTM D4052	g/ml	0.887
Kinematic Viscosity, 100°C	ASTM D445	cSt	18.6
Kinematic Viscosity, 40°C	ASTM D445	cSt	161.8
Viscosity Index (VI)	ASTM D2270	-	130
CCS Viscosity, -15°C	ASTM D5293	cP	7500
Base Number, TBN	ASTM D2896	mg KOH/g	8.5
Sulfated Ash	ASTM D874	% w/w	1.0
Pour Point	ASTM D5950	°C	-30
Flash Point, COC	ASTM D92	°C	230

Health and safety

Protect the environment while disposing of used product. Used lubricants should be collected at specific points to ensure they do not pollute the environment. Do not mix with solvents, brake fluids, antifreeze fluids and water, to allow for proper handling.

30 January 2025

This data sheet provides basic information on the product as at the date of drafting. For further information regarding applications, please contact EKO ABEE Technical Support, tel. +30 210 5509 511.

Advice on safe handling is provided in the Safety Data Sheet.